



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
Beton normal 2.1	17671.459	501704.4	28.39	5183.15	0.014

Stress v.s. Strain



19-01-2022-004

Q.C. Dept. : Lilis E, ST, MT

Tester : \_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
1 bk 1,5,2	17671.459	492003.6	27.84	5382.11	0.014

Stress v.s. Strain



20/01/2022-002

Q.C. Dept. :   
Viles Z, SFMT

Tester : \_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
1 bk 1,5.3	17671.459	464937.7	26.31	4462.42	0.014

Stress v.s. Strain



20/01/2022-003

Q.C. Dept. :  Lilis Z, ST.MT

Tester : \_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
2 bk 2.1	17671.459	491166.3	27.79	4261.18	0.014

Stress v.s. Strain



20/01/2022-004

Q.C. Dept. :

*Lilis E.S., MT*

Tester :

\_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : <http://www.itny.ac.id>


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
2 bk 2.2	17671.459	566197.8	32.04	5904.82	0.014

Stress v.s. Strain



20/01/2022-005

Q.C. Dept. : Lilis E, ST, MT

Tester : \_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
2 bk 2.3	17671.459	583870.6	33.04	6058.69	0.014

Stress v.s. Strain



20/01/2022-006

Q.C. Dept. :   
Lilis Z. S.M.T

Tester : \_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id.


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
2 bk 2,5.1	17671.459	551789.5	31.22	5011.26	0.014

Stress v.s. Strain



20/01/2022-007

Q.C. Dept. :   
Lili Z. R. M.

Tester : \_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
2 bk 2,5.2	17671.459	484040.5	27.39	5332.11	0.014

Stress v.s. Strain



20/01/2022-008

OC Dept.  Lili Z. S. Mr

Tester :





# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
2 bk 2,5.3	17671.459	474815.0	26.87	3997.78	0.014

Stress v.s. Strain



20/01/2022-009

OC Dent •  Ulis E, ST, MT

Tactar • \_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
2 bk 3.1	17671.459	522731.5	29.58	5546.67	0.014

Stress v.s. Strain



20/01/2022-010

OC Dept. :   
Lilis E, ST, MT

Tactan



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
2 bk 3.2	17671.459	573628.1	32.46	5528.85	0.014

Stress v.s. Strain



20/01/2022-011

O.C. Dept. :

  
Lilis Z, ST, MT

Tester :



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
2 bk 3.3	17671.459	628625.5	35.57	5327.13	0.014

Stress v.s. Strain



20/01/2022-012

OC Dept.  Lilis E. ST, MT

Tastan



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
Beton normal 1.1	17671.459	463440.5	26.23	4059.63	0.014

Stress v.s. Strain



19-01-2022-001

Q.C. Dept. :   
Lilis E, ST, MT

Tester : \_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
Beton normal 1.2	17671.459	468332.7	26.50	4219.51	0.014

Stress v.s. Strain



19-01-2022-002

Q.C. Dept. :   
Lilis E, ST, MT

Tester : \_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
Beton normal 1.3	17671.459	409821.4	23.19	4377.48	0.014

Stress v.s. Strain



19-01-2022-003

Q.C. Dept. :   
Lilis Z, ST, MT

Tester : \_\_\_\_\_



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 20/01/2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
1 bk 1,5.1	17671.459	450386.9	25.49	4701.84	0.014

Stress v.s. Strain



20/01/2022-001

Q.C. Dept. :

  
Lilis Z, ST, MT

Tester :





# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
1 bk 3.3	17671.459	461338.0	26.11	4780.93	0.014

Stress v.s. Strain



19-01-2022-021

Lilis E, ST, MT



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
1 bk 3.2	17671.459	461452.1	26.11	4662.34	0.014

Stress v.s. Strain



19-01-2022-020

  
Lilis E, ST, MT



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
1 bk 3.1	17671.459	441106.0	24.96	4600.14	0.014

Stress v.s. Strain



19-01-2022-019

  
Lilis S. ST. MR



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : <http://www.itny.ac.id>


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
2 bk 1,5.3	17671.459	552060.4	31.24	5300.65	0.014

Stress v.s. Strain



19-01-2022-018

Lilis Z, S.T.



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
2 bk 1,5.2	17671.459	524930.8	29.71	5037.88	0.014

Stress v.s. Strain



19-01-2022-017

  
Lilis E, ST.MT



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
2 bk 1,5.1	17671.459	536233.8	30.34	5026.27	0.014

Stress v.s. Strain



19-01-2022-016

  
Agus Z, ST, MT



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
1 bk 2,5.3	17671.459	448546.4	25.38	4501.33	0.014

Stress v.s. Strain



19-01-2022-015

  
Lilis E, ST, MT



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022


Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
1 bk 2,5.2	17671.459	457463.6	25.89	4687.35	0.014

Stress v.s. Strain



19-01-2022-014

  
Lilis Z, ST, MT





# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
1 bk 2,5.1	17671.459	497994.6	28.18	4906.28	0.014

Stress v.s. Strain



19-01-2022-013

  
Lilis S, ST, MT



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area mm <sup>2</sup>	Max Force N	Compression Strength N/mm <sup>2</sup>	Young Modulus N/mm <sup>2</sup>	Elongation mm
1 bk 2.3	17671.459	478364.0	27.07	3152.31	0.014

Stress v.s. Strain



19-01-2022-012

Lilis Z, ST, MT



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
1 bk 2.2	17671.459	359140.2	20.32	3581.04	0.014

Stress v.s. Strain



19-01-2022-011

*Lilis B. ST. MT*



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : [info@itny.ac.id](mailto:info@itny.ac.id) Home Page : <http://www.itny.ac.id>


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
1 bk 2.1	17671.459	439329.0	24.86	4538.76	0.014

Stress v.s. Strain



19-01-2022-010

  
Lilis E, ST, MT



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
Beton normal 3.3	17671.459	437745.0	24.77	3794.58	0.014

Stress v.s. Strain



19-01-2022-009

  
Lilis E, ST, MT



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
Beton normal 3.2	17671.459	484053.7	27.39	4838.55	0.014

Stress v.s. Strain



19-01-2022-008

Lilis E. S. M.



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
Beton normal 3.1	17671.459	450180.9	25.48	4086.31	0.014

Stress v.s. Strain



19-01-2022-007

  
Lilis Z, ST, MT



# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
Beton normal 2.3	17671.459	435894.5	24.67	4053.20	0.014

Stress v.s. Strain



19-01-2022-006

Lili's Z, ST, MT





# LABORATORIUM BAHAN STRUKTUR ITNY

Jl. Babarsari Caturtunggal, Depok, Sleman Yogyakarta 55281 - Telp. (0274) 485390, 486986, 487540  
Fax. (0274) 487249 E-mail : info@itny.ac.id Home Page : http://www.itny.ac.id


## TEST REPORT

Test NO. : 19-01-2022

Test Description :

Specimens	Area $\text{mm}^2$	Max Force N	Compression Strength $\text{N/mm}^2$	Young Modulus $\text{N/mm}^2$	Elongation mm
Beton normal 2.2	17671.459	425312.1	24.07	4145.53	0.014

Stress v.s. Strain



19-01-2022-005

  
Lilir E, ST.MT